

# SILKON220

## CASTABLE REFRACTORY



## Characteristic

SILKON220 is calcium silicate and bauxite based castable refractory inert to liquid aluminium and its alloys. It is a high strength material offering high resistance to erosion and mechanical damage. SILKON220 shapes are pre-fired supplied ready for installation.

## Application

- Transfer Launders
- Casting launders
- Funnels
- Filter boxes

## Composition

- AL2O3 - 57%
- SiO2 - 32%
- CaO - 7%

## Physical Properties

- Bulk density 2100kg/m<sup>3</sup>
- Cold crushing strength 40Mpa
- Maximum service temperature 1300°C

## Advantages

- ✓ Dimensionally stable
- ✓ Thermal shock resistant

## Advantages

- ✓ Non-wetting

# SILKON220

## CASTABLE REFRACTORY



## Characteristic

SILKON220 is calcium silicate and bauxite based castable refractory inert to liquid aluminium and its alloys. It is a high strength material offering high resistance to erosion and mechanical damage. SILKON220 shapes are pre-fired supplied ready for installation.

## Application

- Transfer Launder
- Casting launders
- Funnels
- Filter boxes

## Composition

- AL2O3 - 57%
- SiO2 - 32%
- CaO - 7%

## Physical Properties

- Bulk density 2100kg/m<sup>3</sup>
- Cold crushing strength 40Mpa
- Maximum service temperature 1300°C

## Advantages

- ✓ Dimensionally stable
- ✓ Thermal shock resistant

## Advantages

- ✓ Non-wetting